
WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: B29D 17/00, G11B 7/26

A1

(11) International Publication Number:

WO 97/36738

(43) International Publication Date:

9 October 1997 (09.10.97)

(21) International Application Number:

PCT/SE97/00559

(22) International Filing Date:

1 April 1997 (01.04.97)

(30) Priority Data:

9601262-0

1 April 1996 (01.04.96)

SE

(71) Applicant (for all designated States except US): TOOLEX ALPHA AB [SE/SE]; P.O. Box 1176, S-172 24 Sundbyberg (SE).

(72) Inventors; and


- (75) Inventors/Applicants (for US only): ÖHMAN, Ove [SE/SE]; Asplunda, Uppsala-Näs, S-755 91 Uppsala (SE). BERING, Lars [SE/SE]; Dianavägen 21, S-183 65 Täby (SE).
- (74) Agent: WINBLAD, Peter; H. Albihns Patentbyrå AB, P.O. Box 3137, S-103 62 Stockholm (SE).

(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report. In English translation (filed in Swedish).

(54) Title: METHOD AND APPARATUS FOR GLUEING DISC ELEMENTS TOGETHER



(57) Abstract

The invention relates to a method and a device for glueing together disc elements (12). An adhesive (28) is applied between two disc elements (12) and they are pressed together by means of a flexible membrane (20) in a press unit (10). The adhesive layer formed between the disc elements (12) is cured, for example by means of UV light in a press unit via a transparent cover (18) or a transparent bottom plate (14).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

ΑL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal .
ΑŪ	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	ltajy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JР	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Method and apparatus for glueing disc elements together

The present invention relates to a method for glueing together thin disc elements, especially substrates for digital audio, video or computer discs, such as compact discs or digital video discs.

When producing certain types of data storage discs, for example so-called digital video discs, with one or more layers of information, two substrate sics of polycarbonate with a thickness of 0.6 mm are normally glued together, with the information layer(s) adjacent to the layer of adhesive joining the discs.

For this purpose there has previously been suggested that a method whereby a string of adhesive is applied at the centre of one of the disc substrates, whereafter the other disc substrate is placed concentrically over it and they are together subjected to a rapid rotation whereupon the adhesive is spread radially outwards over the facing surfaces of the disc substrates pulling these together. This process is rapid but requires a great excess of adhesive to function satisfactorily. This method can most closely be characterized as so-called "spincoating" of a protective coating layer of a compact disc, and requires completely flat substrate discs or flat holders during the subsequent curing.

In another suggested method of glueing, the adhesive is applied to one of the discs by means of a printing process, for example screen printing, whereafter the discs are brought together. This method does not waste the adhesive and the application can be carried out very rapidly. However, there is a certain risk that air enclosures will form when the discs are brought together and there is a risk of a risk for breakdown of the printing system should the screen printing blanket rupture.

5

10

15

20

One purpose of the present invention is to suggest a glueing method which prevents the occurrence of excess adhesive and air enclosures in the adhesive layer between the discs.

- For this purpose, the process according to the invention is characterized by the 5 following steps:
 - a) applying an adhesive to one side of a first disc element,
 - b) applying a second disc element centered and aligned with the adhesive coat element.
 - c) that the disc elements are pressed together in a press unit, and
 - d) that a thin adhesive layer formed by compression between the disc elements is cured.
- By carefully dosing and applying an adhesive of suitable viscosity, it is possible 15 to avoid the troublesome removal of excess adhesive, and this, in combination with a suitable compression pressure and curing, prevents the occurrence of air enclosures between the disc elements.
 - The curing of the adhesive layer can be effected in the press unit and/or at a location outside it, for example by irradiating the adhesive layer with ultraviolet light.
 - According to a particularly preferred embodiment of the method according to the invention, a radially outer annular edge area of the disc elements, and preferably also a radially inner area of the same, are subjected to UV light during the compression phase of the disc element, whereby the adhseive is immediately cured at the outer and inner peripheral areas, thereby effectively preventing adhesive from leaking out from the gap between the disc elements.

10

20

The present invention also relates to a device for glueing together thin disc elements, especially substrates for digital audio, video or computer discs, such as compact discs or digital video discs. The device is characterized by a pressure chamber housing comprising; firstly, a bottom plate supporting one side of the disc elements which are laid centered and coinciding on top of each other, secondly, a flexible pressure membrane, arranged to be able to lie in contact against the other side of the disc elements, thirdly, a cover which, together with the membrane defines a pressure chamber, and fourthly, means for pressurizing the pressure chamber with a pressure medium.

10

5

In a suitable embodiment, the cover or the bottom plate is made transparent to permit UV irradiation of the adhesive layer between the disc elements which have been pressed together. This device provides an effectively coordinated glueing together and curing of the disc elements without any problem with excess adhesive and air enclosures.

15

Additional characteristics of the device according to the invention are disclosed in the dependent claims.

20

The invention will be described in more detail below with reference to the accompaying drawing in which:

25

Figure 1 shows schematically a cross-section through a pressing device for glueing together two disc elements according to a first embodiment of the invention, in a phase immediately prior to pressing together; and

Figure 2 shows schematically a second embodiment of the device

according to the invention.

30

In Figure 1, 10 generally designates a pressing unit intended for glueing together two relatively thin (0.6 mm thick) disc substrates 12 of polycarbonate for digital so-called DVDs. The press unit 10 comprises a bottom plate 14, a pressure

chamber wall 16, a cover 18 and a flexible pressure membrane 20 fixed in the wall 16. The cover 18 and the membrane 20 are made transparent for ultraviolet light. Between the cover 18 and the membrane 20 there is defined a pressure chamber 22 designed to be pressurized with compressed air for example via an inlet 24.

The diaphragm or screen 26 for UV light is associated with the press unit 10. It can be integrated with the press unit 10 or with a UV light source (not shown). The diaphragm 26 can provide desired screening off of UV light directed towards the press unit 10 when curing an adhesive layer between the disc substrates 12.

The device in Figure 1 is intended to be used in the following manner.

A well-defined amount of adhseive 28, for example an adhesive of epoxy type, is applied on top of the lower disc substrate 12 in a ring shape, whereafter the upper disc substrate 12 is applied centered over the lower substrate 12. This adhesive application phase can be carried out either in a separate step outside the press unit or in the same. The cover 18 is thereafter put in place and an external compressed air source (not shown) is connected, whereupon compressed air is fed into the pressure chamber 22 via the inlet 24 to exert a suitably adapted pressure on the flexible membrane 20 for the desired compression of the disc substrates 12 so that the adhesive 20 is pressed out towards an outer peripheral edge 30 of the substrates 12 and in towards an inner edge 32 or to an annular groove (not shown) located somewhat radially outwards from said edge 32. This annular groove is normal in CDs. Directly after the compression phase, when a uniform, homogeneous and air enclosure free adhesive layer is formed between the disc substrates 12, the adhesive layer is subjected to UV light via the transparent cover 18 in the membrane 20 as shown by the arrows A in Figure 1 for curing of the adhesive layer. It is, however, an advantage during the compression phase to allow a portion of the adhesive curing UV light to irradiate the outer and inner adhesive layer limiting edge areas 30, 32 of the disc substrates 12, so that the

5

10

15

20

25

adhesive layer is thereby rapidly cured at these edge areas to prevent leakage of adhesive when the discs are pressed together. This edge irradiation of the adhesive layer with UV light is indicated with the arrows B in Figure 1 and can be achieved by the diaphragm 26 blocking off further UV light A until the edge areas of the adhesive layer have been cured, whereafter the diaphragm 26 can be opened or removed to UV irradiate the rest of the adhesive layer. The disc substrates 12 can then be removed from the press unit 10 and possibly be after cured in another location if so required. The glueing process can then be repeated.

10

15

5

Figure 2 shows an alternative embodiment of the press unit 10 according to the invention. The difference in principle is only that the bottom plate 12 in this case is transparent and that the UV rays A, B come from below, and the flexible membrane 20 can be made in a material which is not penetrable by UV light, since it is on the side of the disc substrate 12 remote from the UV source. Otherwise the working principle can be identical to that described in connection with Figure 1.

20

25

The invention is not limited to the embodiments described above. Rather, it can be varied within the scope of the following claims. For example it is possible within the scope of the invention thanks to the thinness of the disc substrates 12 in combination with an easily flowable, low viscosity adhesive, to get it to flow out to a large extent itself and with the aid of the capillary force to fill out most of the space between the disc substrates, so that only a relatively small compression pressure is required to be exerted by the press unit 10 on the disc substrates 12 and the adhesive.

5

10

20

25


30


Claims

- 1. Method for glueing together thin disc elements (12), especially substrates for digital audio, video or computer discs, such as compact disc or digital video discs, characterized by the following steps:
 - a) applying an adhesive (28) to one side of a first disc element (12),
 - b) applying a second disc element (12) centered and aligned with the adhesive coat element (12),
 - c) pressing the disc elements (12) together in a press unit (10), and
 - d) curing a thin adhesive layer formed by compression between the disc elements (12).
- 2. Method according to Claim 1, characterized in that the adhesive layer is cured in the press unit (10) by irradiation of the layer by ultraviolet light.
 - 3. Method according to Claim 1 or 2, characterized in that a radially outer, annular edge area (30) of the disc elements (12) is irradiated with ultraviolet light during the compression phase of the disc elements.
 - 4. Method according to one of Claims 1-3, characterized in that a radially inner area (32) of the disc elements (12) is irradiated with ultraviolet light during the compression phase of the disc elements.
 - 5. Device for glueing together thin disc elements (12), especially substrates for digital audio, video and computer discs, such as compact disc or digital video discs, characterized by a pressure chamber housing (10) comprising firstly a bottom plate (14) supporting one side of the disc elements (12) which are laid centered and coinciding on top of each other, secondly a flexible pressure membrane (20), arranged to be able to lie in contact against the other side of the

disc elements (12), thirdly a cover (18) which, together with the membrane (26) defines a pressure chamber (22), and fourthly means (24) for pressurizing the pressure chamber (22) with a pressure medium.

- 6. Device according to Claim 5, characterized in that the cover (18), or alternatively the bottom plate (14) is made transparent to permit UV irradiation of the adhesive layer between the disc elements (12) pressed together.
 - 7. Device according to Claim 6, in which the cover (18) is UV-transparent, characterized in that the membrane (20) is UV-transparent.
 - 8. Device according to one of Claims 1-6, characterized in that the membrane (20) is anchored in a side wall (16) of the pressure chamber housing (10).
- 9. Device according to one of Claims 6-8, characterized in that that side of the pressure chamber housing (10) which has a transparent cover (18) or alternatively a transparent bottom plate (14) is coordinated with a diaphragm means (14) for bringing off ultraviolet light directed towards the disc elements.





International application No.

DCT.	/c=	97/	በበ559	3

		FC1/3L 3//	00000	
A. CLASS	SIFICATION OF SUBJECT MATTER			
ľ	229D 17/00, G11B 7/26 o International Patent Classification (IPC) or to both to	national classification and IPC		
	S SEARCHED			
	ocumentation searched (classification system followed to	oy classification symbols)		
IPC6: G	 			
I	ion searched other than minimum documentation to the I, NO classes as above	ne extent that such documents are included	in the fields searched	
<u> </u>				
Electronic da	ta base consulted during the international search (narr	e of data base and, where practicable, searc	ch terms used)	
C. DOCUI	MENTS CONSIDERED TO BE RELEVANT			
Category*	Citation of document, with indication, where ap	propriate, of the relevant passages	Relevant to claim No.	
X	Orbit Search Service, File WPAT Accession number 86-262103/ (RICOH KK), J61190738, 86.0 abstract	40.	1-2	
A,P	Orbit Search Service, File WPAT Accession number 97-170864/ (PIONEER ELECTRONIC CORP ET JP09035335, 97.02.07 (9716) abstract	16, AL).	1-2	
X Further	r documents are listed in the continuation of Bo	x C. See patent family anne	х.	
"A" document to be of p	ategories of cited documents: t defining the general state of the art which is not considered particular relevance rument but published on or after the international filing date	"T" later document published after the int date and not in conflict with the appli the principle or theory underlying the "X" document of particular relevance: the	cation but cited to understand invention	
"L" document cited to e	t which may throw doubts on priority claim(s) or which is stablish the publication date of another citation or other cason (as specified)	considered novel or cannot be considered novel or cannot be considered step when the document is taken along	ered to involve an inventive	
"O" document means "P" document	t referring to an oral disclosure, use, exhibition or other t published prior to the international filing date but later than ty date claimed	Y document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art		
	actual completion of the international search	'&' document member of the same patent Date of mailing of the international s		
18 July	1007	19.07	-	
	nailing address of the ISA/	Authorized officer		
Swedish Pa				
	5-102 42 STOCKHOLM 5. +46 8 666 02 86	Johan von Döbeln Telephone No. + 46 8 782 25 00		
	/210 (second sheet) (July 1992)	1 40 6 762 23 UU		

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 97/00559

		PC1/3E 9//	00339
C (Continu	ation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant	Relevant to claim No	
A	Orbit Search Service, File WPAT, Accession number 89-342881/47, (MATSUSHITA ELEC IND KK), J01253846, 89.10.11 (8947), abstract		1,5
ŀ			
1	•		
1			
ļ			
	•		
-			
ļ			
-			
1			